



ECCOBOND D125F-DR

March 2012

PRODUCT DESCRIPTION

ECCOBOND D125F-DR provides the following product characteristics:

Technology	Epoxy
Appearance	Dark red
Components	One-component
Product Benefits	<ul style="list-style-type: none"> • No stringing • Low water absorption • High hot strength • High speed dispensing • High yield • No sag during cure
Cure	Heat Cure
Application	Surface mount adhesive
Operating Temperature	-40 to 105 °C
Typical Assembly Applications	Chip capacitors, Chip resistors, SOTs, SOICs and PLCCs

ECCOBOND D125F-DR surface mount adhesive is designed for use in high-speed pneumatic and positive displacement dispensers. This one component adhesive is formulated to prevent component movement during board handling and cure. ECCOBOND D125F-DR is the red colored version of ECCOBOND D125F.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, Brookfield , ASTM D2393, mPa·s (cP):	
Speed 1 rpm	1,750,000
Speed 10 rpm	350,000
Plastic Viscosity (Casson) Cone & Plate, mPa·s (cP)	
Calculated Yield (Casson) Cone & Plate, N/m ²	2,700
Density, ASTM D792, g/cm ³	1.275
Hegman Fineness, μm	<50
Shelf Life @ 4°C (from date of manufacture), months	3
Flash Point - See MSDS	

TYPICAL CURING PERFORMANCE

IR or Convection Conveyor Oven

20 minutes @ 100°C or
2.5 minutes @ 120°C or
1.5 minutes @ 150°C

Convection Box Oven

30 minutes @ 100°C or
10 minutes @ 120°C or
5 minutes @ 150°C

Note: A ramp up temperature of not more than 1°C per second should be used.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties:

Hardness, Shore D, ASTM D2240	>80
Glass Transition Temperature, ASTM D3418, °C	85
Coefficient of Thermal Expansion , ASTM D3386:	
Below Tg, 10 ⁻⁶ /°C	58
Degree of Conversion by DSC @ 25 °C, %	>90
Linear Shrinkage on Cure, ASTM D2566, %	0.5
Thermal Conductivity, ASTM D-2214, W/(m-K)	0.3

Electrical Properties:

Dielectric Constant @ 1 MHz, ASTM D150	3.5
Volume Resistivity@ 25°C, ASTM D257, ohm-cm	>1×10 ¹⁴

TYPICAL PERFORMANCE OF CURED MATERIAL

Tensile Lap Shear Strength , ASTM D1002:		
Aluminum to aluminum @ 25 °C	N/mm ²	>8
	(psi)	(>1,160)

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

THAWING:

1. Allow material to reach room temperature before use.

DIRECTIONS FOR USE

1. ECCOBOND D125F-DR is best suited for dispensing, pin transfer or stencil printing application method.
2. Equipment set-up and related product information is available from your Henkel Corporation support group.



Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : 4 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation and its affiliates ("Henkel") specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel products. Henkel specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

All trademarks in this document are trademarks and/or registered trademarks of Henkel in the US and elsewhere.

Reference **N/A**